

## СПЕЦИФИКАЦИЯ

<b>НАИМЕНОВАНИЕ ПРОДУКЦИИ</b>
<b>Chlorinated Polyethylene CPE 135A</b> <b>хлорированный полиэтилен</b>

ITEM	SPECIFICATION
Chlorine content %	35
Volatiles %	0.22
Heat of fusion J/g	0.9
Sieving remainder (0.8mm sieve)	1.2
Shore hardness (A)	58
Impurities pieces/100g	20
Time of stability Minutes (165°C)	16
Bulk density g/ml	0.56
Ca+ content %	1.9
Tensile strength Mpa	12.1
Elongation at break %	699
Viscosite Mooney/Mooney viscosity ML(1+4)125°C	87.2