



ក្រុមហ៊ុនយូនម៉េងក្រុប KHUN MENG GROUP CO., LTD.

ការិយាល័យផ្ទះលេខ 176 មហាវិថីមេរៀសេទុង សង្កាត់ទំនប់ទឹក ខណ្ឌចំការមន ភ្នំពេញ

TEST REPORT

Shipment/Delivery: SUMSTAR GROUP CORP
 22/F TOWER A, TEAM CENTER, SOUTH OF SCIENTIFIC PARK,
 DATUN RD., CHAOYANG DISTRICT, BEIJING, P.R CHINA
 TEL: +86 10 66573006 FAX: +86 10 66573001
 Email: hujuebin@sumstar.com

Date Tested: 01 August 2013
 Product Type: CSR – L
 Number of Sample: 3

No	Parameter	Unit	Properties					Specification
			1	2	3	AVG	STDEV	
1	Dirt retained on 44 μm aperture	% wt	0.003	0.003	0.004	0.003	0.005	Max 0.004
2	Ash Content	% wt	0.21	0.20	0.20	0.20		Max 0.21
3	Nitrogen	% wt	0.36	0.39	0.39	0.38		Max 0.39
4	Volatile matter	% wt	0.18	0.20	0.17	0.18		Max 0.20
5	Wallace rapid plasticity (Po)	-	47	47	48	47		Min 47
6	Plasticity retention index (PRI)	%	79.8	79.8	75	78.2		Min 75

Authorized by: